



STRING REINFORCED POLYETHYLENE SRP 20BB & SRP 30BB

Properties	Test Method	SRP 20BB	SRP 30BB
Appearance		Black/Black	Black/Black
Weight Per MSF (lbs)		76	140
Thickness (Nominal)		20 mil	30 mil
Elongation @ Max Load % Diagonal A Diagonal B	ASTM D7003	809% 697%	726% 748%
Grab Tensile (lbs) Diagonal A Diagonal B	ASTM D7004	159 160	220 220
Trapezoidal Tear (lbs) Diagonal A Diagonal B	ASTM D4533	76 72	144 146
Hydrostatic Resistance	ASTM D751, Procedure A	177 psi	142 psi

Note: Test results were compiled by an independent laboratory. Results listed are the mean results of these tests.